

# Refined Impregnation Pitch for Graphite Electrode & block

**RBP-85** *Your first choice for impregnation pitch*  
**Refined Impregnation Pitch**

## Superiorities for production

- Good penetration
- Better percentage weight gain and coke yield
- Significantly improved flexural strength and reinforcing



Spec	RBP-85
TI (%)	28±5
QI (%)	Max.0.3
F.C. (%)	Min.50
Ash (%)	Max.0.1
Softening Point (°C)	85±5
Viscosity at 200°C (cps)	Max.50

*\*Packaging : RBP-85 can be supplied in solid, packed in 25kg bags.*



China Steel Chemical Corp. ([www.csc.com.tw](http://www.csc.com.tw))  
25th FL.,88 Chengong 2nd Rd, Qianzhen, Kaohsiug, Taiwan, R.O.C  
Contact window: Jason Wu Tel:886-7-3383515#39286 Email:[d008@e-csc.com.tw](mailto:d008@e-csc.com.tw)